



ASTM INTERNATIONAL

## Silicon Metal Standard

ASTM A922:2020



Designation: A922 – 05 (Reapproved 2020)

## Standard Specification for Silicon Metal<sup>1</sup>

This standard is issued under the fixed designation A922; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers several grades of silicon metal.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard. The SI equivalents of inch-pound units given may be approximate.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

A1025/A1025M Specification for Ferrous Alloys and Other Alloying Materials, General Requirements

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials

E60 Practice for Analysis of Metals, Ores, and Related Materials by Spectrophotometry

E360 Test Methods for Chemical Analysis of Silicon and Ferrosilicon (Withdrawn 2006)<sup>3</sup>

### 3. General Conditions for Delivery

3.1 Materials furnished to this specification shall conform to the requirements of Specification A1025/A1025M, including any supplementary requirements that are indicated in the

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved March 1, 2020. Published March 2020. Originally approved in 1993. Last previous edition approved in 2015 as A922 – 05 (2015). DOI: 10.1520/A0922-05R20.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

purchase order. Failure to comply with the general requirements of Specification A1025/A1025M constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification A1025/A1025M, this specification shall prevail.

### 4. Chemical Composition

4.1 The grades shall conform to the requirements as to the chemical composition specified in Table 1.

4.2 The manufacturer shall furnish an analysis of each shipment showing the percentage of each element specified.

4.3 Upon request of the purchaser, the manufacturer shall furnish an analysis of any trace elements on a schedule mutually agreed upon between the supplier and the purchaser.

### 5. Size

5.1 The various grades are available in sizes listed in Table 2.

5.2 The sizes listed in Table 2 are typical as shipped from the manufacturer's plant. The various grades can exhibit different degrees of friability; therefore, some attrition may be expected in transit, storage, and handling. A quantitative test is not available for rating relative friability of silicon metal. A code system has been developed, therefore, for this purpose, and a number rating for each product type is shown in Table 3. Definitions applicable to these code numbers are given in Specification A1025/A1025M.

### 6. Chemical Analysis

6.1 The chemical analysis of the material shall be made in accordance with the procedure for silicon metal as described in Test Methods E360 or alternative methods that will yield equivalent results.

6.2 If alternative methods of analysis are used, in case of discrepancy, Test Methods E360 shall be used for referee.

6.3 Where a method is not given in Test Methods E360 for the analysis for a particular element, the analysis shall be made in accordance with a procedure agreed upon between the manufacturer and the purchaser.

NOTE 1—For further information, see Practices E50 and E60.



TABLE 1 Chemical Requirements

Element	Composition %		
	Grade A	Grade B	Grade C
Silicon	>98.00	89.00 to 97.99	80.00 to 88.99
Iron	...	4.00 max	4.00 max

TABLE 2 Standard Sizes and Tolerances<sup>A</sup>

Standard Sizes	Tolerances	
8 by 2 in. (200 by 50 mm)	60 lb (27.2 kg) lump, max	10 % max, passing 2 in. (50 mm) sieve
6 in. (150 mm) by down	10 % max, retained on 6 in. (150 mm) sieve	12 % max, passing 8 M sieve
4 in. (100 mm) by down	10 % max, retained on 4 in. (100 mm) sieve	12 % max, passing 8 M sieve
4 by ½ in. (100 by 12.5 mm)	10 % max, retained on 4 in. (100 mm) sieve	10 % max, passing ½ in. (12.5 mm) sieve
4 by 1 in. (100 by 25 mm)	10 % max, retained on 4 in. (100 mm) sieve	10 % max, passing 1 in. (25 mm) sieve
3 by ½ in. (75 by 12.5 mm)	12 % max, retained on 3 in. (75 mm) sieve	15 % max, passing ½ in. (12.5 mm) sieve
3 by 1 in. (75 by 25 mm)	12 % max, retained on 3 in. (75 mm) sieve	15 % max, passing 1 in. (25 mm) sieve
2 by ½ in. (50 by 12.5 mm)	12 % max, retained on 3 in. (75 mm) sieve	15 % max, passing ½ in. (12.5 mm) sieve
1 in. (25 mm) by No. 8	10 % max, retained on 1 in. (25 mm) sieve	10 % max, passing No. 8.
1 in. (25 mm) by down	12 % max, retained on 1 in. (25 mm) sieve	20 % max, passing No. 8.
No. 8 by down	10 % max, retained on No. 8 sieve	...
No. 20 by down	10 % max, retained on No. 20 sieve	...

<sup>A</sup> Tolerances and sieve sizes defined by Specification E11.

TABLE 3 Friability Ratings

Product Grade	Proposed Friability Rating
A	5
B	5
C	5

## 7. Keywords

### 7.1 silicon; silicon metal

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*